

**Egenvægtstabel for armeringsjern og net, kg.
/ lbm.**

Stangjern.

Diam.	Ø-jern	Y-jern	T-jern
6	0,222	0,23	0,23
8	0,395	0,41	0,41
10	0,616	0,64	0,64
12	0,888	0,92	0,91
14	1,208	1,25	1,24
16	1,578	1,63	1,62
18	1,998	2,06	2,06
20	2,466	2,54	2,54
22	2,984	3,07	3,07
25	3,853	3,96	3,97
35	7,55	7,78	7,78

Net 2,35 * 5 m. Kun Y jern

Diam.	Masker	Vægt-net	Vægt m ²
4	100/100	23,50	2,00
4	150/150	15,80	1,34
4	200/200	11,80	1,00
5	100/100	36,60	3,11
5	150/150	24,60	2,09
5	200/200	18,30	1,56
6	100/100	52,70	4,49
6	150/150	35,50	3,02
6	200/200	26,40	2,25
8	100/100	93,80	7,98
8	150/150	63,30	5,39
8	200/200	46,90	3,99
10	100/100	146,50	12,47
10	150/150	98,70	8,40
10	200/200	73,30	6,24
12	100/100	210,60	17,92
12	150/150	142,00	12,09
12	200/200	105,40	8,97
14	100/100	286,20	24,36
14	150/150	193,00	16,43
14	200/200	143,20	12,19

16	100/100	372,50	31,70
16	150/150	251,70	21,42
16	200/200	186,90	15,91